Ricochet™ Flexible Wall Protection

Clarity - 18 Colorways

PHYSICAL PROPERTIES

| Trim to 48" | | |
|--|--|--|
| 15-yd rolls | | |
| 0.032 | | |
| Heavy Polyester/ Cotton knit | | |
| N/A | | |
| Reverse hang, Random match | | |
| Class "A" rated ASTM E-84; NFPA 286 | | |
| | | |

ENVIRONMENTAL & HEALTH

| Indoor Air | Meets California Section 01350 |
|---------------------|---|
| Fungal Resistant | ASTM G-21 |
| Bacterial Resistant | ASTM G-22 |
| HPD | third-party classified |
| EPD | third-party classified |
| NSF/ANSI 342 | third-party certified, ask distributor |

CHEMICAL

| Chemical Resistance ASTM D-1308, Spot test covered 3.1.1 | |
|---|---|
| Cleaning Agents | |
| Tide w/H20 | |
| Virex | |
| Ammonia | |
| Isopropyl Alcohol | |
| Goof Off | |
| Fantastik | |
| Lysol | |
| Hydrogen Peroxide | |
| Bleach | |
| Methyl Ethyl Ketone | _ |
| Results: No change in Ricochet surface from exposure to these agents. | |

CLEANING

| P | Cleaning ASTM F-793, SECTION 7.5 |
|----|---|
| S | staining Agents |
| (| Grape Juice |
| ٨ | Austard |
| Е | Black Sharpie |
| lı | nk Pen |
| Е | Betadine |
| S | Shoe Polish |
| L | ipstick |
| Е | Black Rubber |
| Е | Brake Fluid |
| S | pray Paint |
| a | Results: Each staining gent above was wiped clean with at least one sted cleaning agent. |

ABRASION

| Abrasion Resistance ASTM D- 4060-14, Taber Method | | |
|---|--|--|
| Test Spec | | |
| CS-10F wheel, 500 gram load @200 cycles | | |
| Weight loss: 0.02% | | |

IMPACT

| | mpact Resistance ASTM D- 420-10, Gardner Method | | |
|---------|--|--|--|
| Pattern | In-Lbs | | |
| Clarity | 100+ | | |

Best stain removal results can be achieved by use of progressively strong, non-abrasive cleaners, and which can be supplemented by use of a soft bristle brush.

OTHER

5 year warranty against manufacturing defects.

Accessories: Coordinating corner guards, top trim and Type II wallcovering (on selected colorways) available. Installs with techniques similar to Type II vinyl wallcovering, including seaming with overlap and double-cut process. See full Installation Instructions.

Sold in 15-yd coreless rolls, one per shipping box (approximately 42 lbs)

IPC.3147/REV.1

